

MARKED UP VERSION TO SHOW CHANGES MADE

In the Specification

Page 15, line 10

In addition, the magnetizing step may be carried out while the thermoplastic binder is at an elevated temperature. This results in an alignment of the magnetic particles with a significant increase in the magnetic strength of the article as compared to the same article magnetized at ambient temperature. See Sawa 4022701 and Ito [6190513] 6190573.